



DM Sourcing Solutions

310C West Westfield Avenue, Roselle Park, NJ 07204 Ph: 973-369-7079 Fax: 973-369-7088

Material Data Sheet

Compound name	Description
LR0702N	Black NBR 70 Shore A

Properties	Unit	Typical value	Test Method
Hardness	Shore A	70	ASTM D2240
Tensile strength	Mpa	≥ 9	ASTM D412
Elongation at break	%	≥ 350	ASTM D412
Tear strength	KN/m	≥ 30	ASTM D624
Temperature Range			
-30 °C ~ +120 °C			

Darrin Oppenheim

Managing Member

Distributed by:

NELSON JAMESON
INC.

800-826-8302 nelsonjameson.com