

MOLYKOTE® 111 Compound

Features & benefits

- Wide service-temperature range (-40°C/-40°F to 200°C/392°F)
- Excellent water resistance
- Compatible with many plastics and elastomers
- Low vapor pressure
- Low volatility
- Meets several global standards for water contact

Composition

- Silicone oil
- Inorganic thickener

Applications

Lubrication for control and pressure plug valves, water softener and faucet valves. Sealant for vacuum and pressure systems and outdoor equipment (also shipboard) subject to washing and harsh environmental exposure, such as meters, electrical service entrance and underground connections. Damping medium for dash pots in electrical and electronic equipment. As an anti-stick and a sealant for transformer gasket and equipment enclosures – it prevents gaskets from sticking to metal and resists weathering and water washout. Also suitable for rubber and plastic O-rings, gaskets and seals.

Certifications

MOLYKOTE® 111 Compound meets several global standards for water contact, including NSF 51, NSF 61, FDA 21 CFR 175.300, Water Regulations Advisory Scheme Approval BS9260 (England), IPL Certificate of Conformity (France), AS/NZS 4020:2018 (Australia), and the hygiene suitability for drinking water contact from HyCert (Germany).

How to use

How to apply

MOLYKOTE® 111 Compound can be applied by hand, specially designed automated equipment, brushing or wiping. Certain designs of grease guns may seize up; test prior to use. A thinner consistency can be achieved by dispersing in solvents such as xylene, mineral spirits and methyl ethyl ketone. MOLYKOTE® 111 Compound can then be applied by brushing, dipping or spraying.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Color		White to light gray; translucent
ISO 2137	Penetration unworked	mm/10	170 to 230
ISO 2137	Penetration; worked 60, max	mm/10	260
CTM 0033A	Bleed 24 hours/200°C (392°F), max	%	0.5
CTM 0033A	Evaporation 24 hours/200°C (392°F), max	%	2.0

⁽¹⁾ISO: International Standardization Organization. CTM: Corporate Test Method; copies of CTMs are available on request.

MOLYKOTE® 111 Compound should not be applied to any surface that will be painted or finished. Such coatings may not adhere to the silicone-treated surface. If contaminated by a silicone coating, parts can be wiped or washed with solvent, washed with detergent, or immersed in an alcoholic potassium hydroxide solution and then rinsed in clear water before painting.

Chemical resistance

MOLYKOTE® 111 Compound is not greatly affected by mineral oils, vegetable oils or air. It is generally resistant to dilute acids and alkalines and to most aqueous solutions.

Because each application may vary in chemical composition, pressure, flow velocity, relubrication requirements and equipment design, it is recommended that the silicone compound be tested before adopting for regular use.

MOLYKOTE® 111 Compound is not to be used with liquid oxygen and should not be used in applications requiring LOX compatibility.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored between 0 and 40°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1997-2021 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.