



Analytical
Laboratory
Menlo
GA, 30731

Nitri-Dex 707, Unsupported Nitrile

ASTM F739 Chemical Permeation for PPE (in minutes)

CHEMICAL	Test Results (in minutes)
acetone	5
toluene	4.8
hexane	53
iso propyl alcohol	143
gasoline	151
methanol	17
sodium hydroxide 50%	>480
hydrochloric acid 37%	>480

comments:

No unusual observations

Distributed by:

NELSON JAMESON
INC.

800-826-8302 nelsonjameson.com