



# SANI-GUIDE

PROPRIETARY INFORMATION  
THIS PRINT MAY NOT BE COPIED  
OR INFORMATION USED IN ANY WAY  
WITHOUT EXPRESS PERMISSION OF PLANT TWO INC.



.04 U. X .085 DEEP RUNNER  
8 PLACES EXTENDING TO  
2.158 DIA.

*Handwritten:* 40-50 MESH  
350-400 MESH



## GRID DETAIL

S DEC./SIDE

FUNCTIONAL	DATE	REV	BY	CHKD	DATE	REV	BY	CHKD
1	1/82	184		2				
2	1/82	184		2				
3	1/82	184		2				

REV	DATE	DESCRIPTION
0	11/07/98	ORIG. R
1	05/13/98	REV. Q1
2	05/31/98	REV. 0
3	05/05/98	EXTEND

SECT. A - A

# Marlex® 1007

LOW DENSITY POLYETHYLENE

This autoclave LDPE homopolymer is tailored for applications that require:

- Excellent flexibility
- Good flow
- Moderate mold release
- Good warpage resistance

This resin meets these specifications:

- ASTM D4976 - PE 113
- FDA 21 CFR 177.1520(c) 2.2, use conditions B through H per 21 CFR 176.170(c)

Typical injection molded applications for 1007 include items such as:

- Housewares
- Tamper evident, snap-on caps
- Wine bottle sleeve caps

NOMINAL PHYSICAL PROPERTIES <sup>(1)</sup>			
	English	SI	Method
Density	---	0.917 g/cm <sup>3</sup>	ASTM D1505
Melt Index, 190/2, 16	---	7.0 g/10 min	ASTM D1238
Tensile Strength at Yield, 2 in/min, Type IV bar	1,300 psi	9 MPa	ASTM D638
Elongation at Break, 2 in/min, Type IV bar	600%	600%	ASTM D638
Flexural Modulus, Tangent - 16:1 span:depth, 0.5 in/min	30,000 psi	200 MPa	ASTM D790
Durometer Hardness, Type D (Shore D)	47	47	ASTM D2240
Vicat Softening Temperature, Loading 1, Rate A	189°F	87°C	ASTM D1525
Brittleness Temperature, Type A, Type I specimen	-87°F	-66°C	ASTM D746

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.

MSDS #240370

Distributed by:

**NELSON JAMESON**  
INC.  
800-826-8302 nelsonjameson.com