

3DM1A C

Transparent, coextruded shrink bag with high barrier properties (PVDC) and Polyethylene sealing layer (PE) for ripening and transport packaging of fresh and processed meat

| Technical data | | Unit | Method | Condition | Value |
|----------------|---|--------------------------------------|--------------|----------------|---------|
| | General data | | | | |
| | Total thickness | µm | DIN 53 370 | | 46 |
| | Grammage | g/m ² | DIN 53 104 | | 91,1 |
| | Shrinkage: | | | | |
| | MD / TD | % | internal | 85°C / 6 sec | 33 / 40 |
| | MD / TD | % | internal | 93°C / 6 sec | 47 / 50 |
| | Permeability | | | | |
| | Vapour (water-permeability) | g/m ² d | DIN 53 122 | 23°C / 85% r.h | <1,0 |
| | Oxygen-permeability | cm ³ /m ² dbar | DIN 53 380 | 23°C / 0% r.h | <20 |
| | Carbon dioxide-permeability | cm ³ /m ² dbar | DIN 53 380 | 23°C / 0% r.h | 30 - 60 |
| | Mechanical properties | | | | |
| | Deterioration (force) | N | DIN EN 14477 | | >5,0 |
| | Application instructions and technical conditions of use | | | | |
| | Min. application temperature (shockfree) | °C | | | -25 |

Revision: 1/20.07.2017

Important advices:

All data given in this data sheet are approximate, based on our current knowledge and relate solely to the unformed material. A liability cannot be derived. Due to the manifold applications and processing possibilities, trials under real conditions are essential. The qualification tests as well as the release of the material, taking into account possible interdependencies between product and packaging material, are under the responsibility of the user. For microwave applications, the filling good as well as the preparation parameters have to be taken into account especially. We reserve the right to change technical data due to technological progress.

Recommended storage conditions:

In original packaging and protected from direct sunlight up to max. one year after delivery at 5-20°C (max. 25°C) and 40-60% r.h. Acclimatization in the packaging room before processing is recommended.

Food approval:

The product complies with EU Regulations and Directives for plastic materials and articles, intended to come into contact with food. Further details are specified in the corresponding Declaration of Compliance (DoC). All Schur Flexibles Dixie packaging materials are produced in accordance to the BRC/IoP global standard.