


[Printer Friendly Version](#)

Bapolene® PP5052 Polypropylene, Injection Grade

[Request additional product information or price quote](#)

Key Features:

Superior balance of stiffness and impact strength

Material Notes:

Polypropylene injection impact copolymer with excellent color and processability. This resin also has a superior balance of stiffness and impact strength. This product meets FDA standards for food contact applications.

Applications: Battery cases, housewares, appliances.

Bapolene® and Bapolan® are registered trademarks of Bamberger Polymers, Inc. Information provided by Bamberger Polymers

Physical Properties	Metric	English	Comments
Density	0.903 g/cc	0.0326 lb/in ³	ASTM D1505
Melt Flow	8.00 g/10 min Load 2.16 kg, Temperature 230 °C	8.00 g/10 min Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	ASTM D-2240
Tensile Strength, Yield	26.9 MPa	3900 psi	2 in/min (50 mm/min); ASTM D638
Elongation at Break	160 %	160 %	2 in/min (50 mm/min); ASTM D638
Elongation at Yield	14.0 %	14.0 %	2 in/min (20 mm/min); ASTM D638
Flexural Modulus	1.21 GPa	175 ksi	Secant @ 1% strain; ASTM D-790
Izod Impact, Notched	1.17 J/cm	2.19 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	84.0 °C	183 °F	ASTM D648

Qualitative Processing Properties

process

Injection Molding

Values reported are typical and should not be interpreted as specifications. Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to our disclaimer and terms of use regarding this information.

Data Properties Disclaimer: Bamberger Polymers shall not be responsible for the applicability or the accuracy of the information contained herein or the suitability of the products described herein for any particular purpose. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made with respect to the products described herein or with respect to the use of the products described herein.

Copyright © 2008-2012 Bamberger Polymers, Inc. All Rights Reserved. Please see our [Legal Information](#)

[Home](#)

Linsey Hahn – President

4/26/2013

Metro Plastics

9175 E 146th St

Noblesville, IN 46060



CERTENE PBM-8 – Polypropylene Impact Copolymer

CERTENE grade PBM-8 complies with FDA regulation 21CFR 177.1520 (a)(3)(i)/(c)3.1+3.2, and most international regulations concerning the use of Polypropylene in contact with food.



April 30, 2013

Lindsey Hahn
Metro Plastics Technologies Inc
9175 East 146th Street
Noblesville, IN 46061

Dear Lindsey,

In response to your request, the components of A. Schulman Inc product **RY-61465 FDA Red (1030313)** meet the conditions and requirements of the following sections of 21 CFR (FDA) regulations:

177.1520(c)(3.1)
178.3297

This product can be used for conditions of use C through G in 21 CFR 176.170(c), Table 2 and can be used in contact with all food types as listed in 21 CFR 176.170(c), Table 1. This product should not be used for holding or packing food while cooking.

This product has a maximum usage level of 30% by weight.

This product is a physical mixture of FDA approved components. Any limitations for use of these components are listed above. If this product is used as an additive or blended with other products, then the final product could have use limitations with food contact. It is the blender's responsibility to make that determination.

This declaration is based on information from our suppliers.

If you need any further regulatory, environmental, safety or health information, please feel free to contact me at 330-668-7343 or Susan_Fizer@us.aschulman.com.

Sincerely,

Susan Fizer
EHS Regulatory Manager