

GRT 362

Distributed by:

NELSON JAMESON
INC.

800-826-8302 nelsonjameson.com

Certificate of Compliance

MATERIAL PROPERTIES

Color:	White
Composition:	Nitrile
Durometer, Shore A:	55-65
Temperature, °F	
Minimum:	-20
Maximum:	+200
Finish Available	Smooth

PHYSICAL PROPERTIES

Tensile Strength, psi:	
Minimum:	1500
Typical:	1700
Elongation, %:	
Minimum:	400
Typical:	450
Avg. Wt. (lbs./sq.yd 1/16" thick):	3.8lbs
Line Call Out:	ASTM D 2000-2BF-615-E034 FDA Standard 21 CFR 177.2600 3-A Dairy Standard 18-02/18-03 Type III & IV

MADE IN THE USA

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material.

- * Values do not constitute specification Limits
- * When approaching the maximum or minimum ratings consult an Applications Engineering
- * For rubber compound only, not fabric