



A1									
Property	Test Method Reference	Values							
		0.50	0.60	0.63	0.70	0.75	0.80	0.90	1.15
Gauge, mil	ASTM D-374								
Ult Tensile MD, psi	ASTM D-882	4,800	4,800	7,000	4,800	4,800	4,800	4,800	4,800
Ult Tensile TD, psi	ASTM D-882	2,700	3,000	4,000	3,200	3,250	3,300	3,500	3,500
Tens Yield MD, psi	ASTM D-882	1,400	1,400	1,400	1,400	1,400	1,400	1,400	1,400
Tens Yield TD, psi	ASTM D-882	1,400	1,400	1,300	1,400	1,400	1,400	1,400	1,400
Ult Elong MD, %	ASTM D-882	360	370	380	380	395	410	430	490
Ult Elong TD, %	ASTM D-882	510	560	500	570	575	580	600	620
1% Modulus MD, psi	ASTM D-882	35,000	33,000	29,000	30,000	34,000	28,000	27,600	27,000
1% Modulus TD, psi	ASTM D-882	35,000	33,000	30,000	30,000	34,000	28,000	27,600	29,000
Tear MD, g	ASTM D-1922	170	230	190	280	305	330	380	420
Tear TD, g	ASTM D-1922	400	450	470	500	525	550	600	700
Puncture, lbs	Internal	6	8	8	10	10	11	12	14
Dart Impact F50, g	ASTM D-1709A	70	80	85	90	95	100	110	130

NOTE: The data presented above is for the product type described and is based on random tests that are not statistically valid. The values should only be used for reference and are not to be used for any type of specification. Berry Global does not monitor these values or manufacture to these values. Please be advised that values are known to change based on normal manufacturing variables such as production line, and lot to lot variations of raw materials. There is no guaranty expressed or implied regarding the use of this information or its suitability for a particular application.