

# CS18H Hot Melt Tape

<b>Product Description</b>	<ul style="list-style-type: none"> <li>• BOPP film coated tape</li> <li>• General purpose packaging tape used for box sealing, splicing and other packaging applications.</li> <li>• Hot melt pressure sensitive adhesive system with high adhesion, and holding power</li> </ul>	
<b>Applications</b>	<ul style="list-style-type: none"> <li>• Multi-purpose packaging tape</li> <li>• Suitable for lightweight carton sealing need</li> <li>• Adheres instantly to variety of surfaces</li> <li>• Edge tear and split resistance</li> </ul>	
<b>Features/Benefits</b>	<ul style="list-style-type: none"> <li>• Economical and utility grade Biaxially Oriented Polypropylene (BOPP) tape</li> <li>• Good Adhesion to fiberboard</li> <li>• No known hazards</li> </ul>	
<b>Construction</b>	Film	Biaxially oriented polypropylene film
	Adhesive	Synthetic rubber
	Color	Clear
<b>Physical Properties</b>	<p>Note: The following technical information and data should be considered representative or typical only.</p>	
	Total Thickness	0.045 ± 0.002 mm (1.8 ± 0.08 mil)
	Film Thickness	0.028 ± 0.001 mm (1.1 ± 0.04 mil)
	Adhesion to steel	0.40 kg/cm (35.2 oz./in)
	Cohesion	10,000 minutes, 73° F (23° C)
	Tensile Strength	3.6 kg (19.8 lbs./in)
	Elongation at Break	100 ~ 180%
<b>Storage</b>	<p>Recommended one-year shelf life from date of dispatch, if kept at moderate temperatures and humidity levels</p>	

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.