



CNM-660.21B

Nylon Gusseted Liner

Key Attributes:

→ A BETTER WAY



Great Strength



Outstanding Thermal Resistance



Outstanding Puncture Resistance



Excellent Tear Resistance



Good Barrier

Excellent Clarity

Distributed by:
NELSON JAMESON
INC.
800-826-8302 nelsonjameson.com

Typical End Uses: Barrier Liners

Attribute		Typical Value	Units	ASTM Test Method
Gauge		3.00	mil	
Yield @ 1mil			in ² /lb	
Haze		11	%	D-1003
Gloss (45°)		70	%	D-2457
Tensile	MD	5,580	psi	D-882
	TD	5,350		
Elongation	MD	740	%	D-882
	TD	780		
Secant Modulus	MD	30,000	psi	D-882
	TD	28,000		
Elmendorf Tear	MD		g	D-1922
	TD			
Dart Impact		1,000	g	D-1709 (method B)
O ₂ TR		3.4	cc/100in ² /24hr (0% RH, 23°C)	D-1434
MVTR		0.4	g/100in ² /24hr (90% RH, 100°F)	F-1249
Creation Date:				03/09/2017

The information provided is a good faith summary of typical film properties but is not meant to be used as a specification, nor as a guarantee of film properties. Users must assume responsibility for fitness of use in their individual applications. In addition, Charter NEX Films, Inc. does not warranty against patent infringement.