


VP 300 PA/PE Coextrusion



	Typical Value	Metric Units	Typical Value	English Units	Test Method
Gauge	70	μm	2.75	mil	ASTM F2251
Yield	0.0147	m ² /g	10354	in ² /lb	/
Elongation /MD	370	%	370	%	ASTM D882
Elongation /TD	370	%	370	%	ASTM D882
Tensile Strength /MD	23	Mpa	3335	PSI	ASTM D882
Tensile Strength /TD	23	Mpa	3335	PSI	ASTM D882
Haze	15	%	15	%	ASTM D1003
COF	0.25		0.25		ASTM D1894
OTR	62	cc/m ² .d (dry)	4	cc/100 in ² .d (dry)	ASTM D3985
WVTR	7	g/m ² .d	0.45	g /100 in ² .d	ASTM F1249
Seal Strength	21	N/15mm	8	lbs/in	ASTM F88

Compliance: This product complies with FDA, KOSHER, CFIA and QS for direct food contact applications.

Storage: This product should be stored in the clean, cool and dry conditions. The shelf life of this product under these condition is 12 months.

Declaration: The technical data contained herein is based on internal testing results and believed to be reliable. Users should make their own judgment and determination of the suitability for their intended applications. Vac Pak assumes no liability whatsoever in connection with the use of information.