



R&D Coshocton Testing Laboratories  
923 Chestnut Street  
Coshocton, Ohio 43812 USA

**TEST REPORT**

**Test Report No:** 2013-4019  
**Report Date:** April 19, 2013  
**Title:** Historical Average Coefficient of Friction Data For Ansell Disposable Nitrile Gloves  
**Products:** Touch N Tuff Styles 92-500 and 92-600  
**Test Method:** ASTM D 1894 (STATIC AND KINETIC COEFFICIENTS OF FRICTION OF PLASTIC FILM AND SHEETING)  
**Instrumentation:** R. J. Harvey Instrument Corp. (F-101 Slip Laminate Device and F-200 Force Gauge)

**Results:**

| Historical Average Data |             |              |
|-------------------------|-------------|--------------|
| Ansell Style Reference  | COF: Static | COF: Kinetic |
| Touch N Tuff® 92-500    | 1.1         | 0.8          |
| Touch N Tuff® 92-600    | 1.2         | 0.9          |

**Reported By:** Paul B. McMorrow - Quality Coordinator, Americas

*This report shall not be reproduced, except in full, without the written approval of Ansell.*

